

### **TECHNICAL DATA SHEET**

DIC



# 1401

#### DESCRIPTION

• 65°Sh Hypalon<sup>®</sup>. Excellent properties and price. Smooth finish and fabric impression.

#### **COLOUR:**

Black

#### FEATURES

 Hypalon<sup>®</sup> rubber sheet with good properties and excellent qualityprice ratio.

#### **APPLICATIONS**

 Gaskets, flanges, applications with weather conditions and/or offshore.

TECHNICAL PROPERTIES			
	VALUE	UNIT	STANDARD
SPECIFIC WEIGHT	1,39 +/- 0,03	g/cm3	UNE 53526
HARDNESS	65 +/- 5	°Sh A	DIN ISO 7619-1
TENSILE STRENGTH	10 min	MPa	UNE-ISO 37
ELONGATION	200 min	%	UNE-ISO 37
COMPRESSION SET (24h/ 70 °C)	35 Mean values	%	UNE-ISO 845-1
WORKING TEMPERATURE	-30/+125	°C	

CHEMICAL RESISTANCE	
OZONE RESISTANCE	EXCELLENT
WEATHER RESISTANCE	EXCELLENT
OIL RESISTANCE	GOOD
ACID RESISTANCE	GOOD
BASE RESISTANCE	GOOD

The technical information contained in this data sheet is the result of performing tests on laboratory samples according to the standards mentioned above. The customer is responsible for evaluating the suitability of the product according to their specific requirements. Values may be updated without prior notice.

#### www.idcrubber.com

Ctra. Artica 16 | 31013 Artica | Navarra (Spain) **T** +34 948 145 388 | F +34 948 126 032 idcrubber@grupoelastorsa.com

## GRUPO 🖪 ELASTORSA