

TECHNICAL DATA SHEET

Ye



1403

DESCRIPTION

• FKM with excellent chemical resistance and temperature resistance up to 250°C.

COLOUR:

Black

FEATURES

 FKM fluoroelastomere rubber sheet with very good chemical and high temperature resistance

APPLICATIONS

- Chemical, acids, hydrocarbons attack and high temperature demand applications, up to 205°C continuous and picks up to 250°C.
- Good gas impermeability and ozone resistance.

TECHNICAL PROPERTIES			
	VALUE	UNIT	STANDARD
SPECIFIC WEIGHT	1,74 +/- 0,03	g/cm3	UNE 53526
HARDNESS	75+/- 5	∘Sh A	DIN ISO 7619-1
TENSILE STRENGTH	5 min	MPa	UNE-ISO 37
ELONGATION	225 min	%	UNE-ISO 37
COMPRESSION SET (24h/70°C)	50 Mean values	%	UNE-ISO 815-1
WORKING TEMPERATURE	-20/+205	°C	

CHEMICAL RESISTANCE	
OZONE RESISTANCE	EXCELLENT
WEATHER RESISTANCE	EXCELLENT
OIL RESISTANCE	EXCELLENT
ACID RESISTANCE	EXCELLENT
BASE RESISTANCE	EXCELLENT

The technical information contained in this data sheet is the result of performing tests on laboratory samples according to the standards mentioned above. The customer is responsible for evaluating the suitability of the product according to their specific requirements. Values may be updated without prior notice.

www.idcrubber.com

Ctra. Artica 16 | 31013 Artica | Navarra (Spain) **T** +34 948 145 388 | F +34 948 126 032 idcrubber@grupoelastorsa.com

GRUPO 🔣 ELASTORSA