

TECHNICAL DATA SHEET

NR-120°C

2410

DESCRIPTION

- 45°Sh grey dynamic. Abrasion of 80 (5N) and high temperature resistance. Various finishes.

COLOUR:

- Grey






FEATURES

APPLICATIONS

TECHNICAL PROPERTIES

| | VALUE | UNIT | STANDARD |
|---------------------|---------------|-------------------|----------------|
| SPECIFIC WEIGHT | 1,13 +/- 0,03 | g/cm ³ | UNE 53526 |
| HARDNESS | 45 +/- 5 | °Sh A | DIN ISO 7619-1 |
| TENSILE STRENGTH | 22 min | MPa | UNE-ISO 37 |
| ELONGATION | 500 min | % | UNE-ISO 37 |
| ABRASION (5N) | 80 max | mm ³ | UNE-ISO 46491 |
| TEAR STRENGTH ANGLE | 35 min | kg/cm | UNE-ISO 34-1 |
| WORKING TEMPERATURE | -30/+120 | °C | |

CHEMICAL RESISTANCE

| | | |
|--------------------|------------|---|
| OZONE RESISTANCE | MODERATE |  |
| WEATHER RESISTANCE | MODERATE |  |
| OIL RESISTANCE | LOW |  |
| ACID RESISTANCE | ACCEPTABLE |  |
| BASE RESISTANCE | ACCEPTABLE |  |

The technical information contained in this data sheet is the result of performing tests on laboratory samples according to the standards mentioned above. The customer is responsible for evaluating the suitability of the product according to their specific requirements. Values may be updated without prior notice.

www.idcrubber.com