

## TECHNICAL DATA SHEET

# CR

# 3922

### DESCRIPTION

- 60°Sh white CR with very good elongation. Smooth, matte, fabric impression and bonding layer.

### COLOUR:

- White






### FEATURES

### APPLICATIONS

#### TECHNICAL PROPERTIES

	VALUE	UNIT	STANDARD
SPECIFIC WEIGHT	1,52 +/- 0,03	g/cm <sup>3</sup>	UNE 53526
HARDNESS	60+/- 5	° Sh A	DIN ISO 7619-1
TENSILE STRENGTH	7 min	MPa	UNE-ISO 37
ELONGATION	500 min	%	UNE-ISO 37
COMPRESSION SET (24h, 70°C)	35 Mean values	%	UNE-ISO 815-1
AGEING HARDNESS (72h, 70°C)	+1 Mean values	° Sh A	DIN ISO 7619-1
AGEING TENSILE STRENGTH (72h, 70°C)	-3 Mean values	%	UNE-ISO 37
AGEING ELONGATION (72h, 70°C)	-7 Mean values	%	UNE-ISO 37
WORKING TEMPERATURE	-30/+110	°C	

#### CHEMICAL RESISTANCE

OZONE RESISTANCE	GOOD	
WEATHER RESISTANCE	GOOD	
OIL RESISTANCE	MODERATE	
ACID RESISTANCE	MODERATE	
BASE RESISTANCE	MODERATE	

The technical information contained in this data sheet is the result of performing tests on laboratory samples according to the standards mentioned above. The customer is responsible for evaluating the suitability of the product according to their specific requirements. Values may be updated without prior notice.

[www.idcrubber.com](http://www.idcrubber.com)