

TECHNICAL DATA SHEET

CR/SBR

3995

DESCRIPTION

- 40°Sh black CR/SBR with good elongation. Smooth, matte, fabric impression and bonding layer.

COLOUR:

- Black






FEATURES

APPLICATIONS

TECHNICAL PROPERTIES

	VALUE	UNIT	STANDARD
SPECIFIC WEIGHT	1,32 +/- 0,03	g/cm ³	UNE 53526
HARDNESS	40 +/- 5	°Sh A	DIN ISO 7619-1
TENSILE STRENGTH	4 min	MPa	UNE-ISO 37
ELONGATION	450 min	%	UNE-ISO 37
COMPRESION SET (24h/70°C)	40 Mean values	%	UNE-ISO 815-1
AGEING HARDNESS (72h/70°C)	-5 Mean values	°Sh A	DIN ISO 7619-1
AGEING TENSILE STRENGTH (72h/70°C)	-15 Mean values	%	UNE-ISO 37
AGEING ELONGATION (72h/70°C)	-40 Mean values	%	UNE-ISO 37
WORKING TEMPERATURE	-20/+100	°C	

CHEMICAL RESISTANCE

OZONE RESISTANCE	MODERATE	
WEATHER RESISTANCE	MODERATE	
OIL RESISTANCE	LOW	
ACID RESISTANCE	MODERATE	
BASE RESISTANCE	MODERATE	

The technical information contained in this data sheet is the result of performing tests on laboratory samples according to the standards mentioned above. The customer is responsible for evaluating the suitability of the product according to their specific requirements. Values may be updated without prior notice.

www.idcrubber.com