

## TECHNICAL DATA SHEET

# CR/SBR

# 3999

### DESCRIPTION

- 70°Sh black CR/SBR. Smooth, matte, fabric impression and bonding layer. Possibility of adding textile inserts.






### COLOUR:

- Black

### FEATURES

### APPLICATIONS

TECHNICAL PROPERTIES			
	VALUE	UNIT	STANDARD
SPECIFIC WEIGHT	1,33 +/- 0,03	g/cm <sup>3</sup>	UNE 53526
HARDNESS	70+/- 5	°Sh A	DIN ISO 7619-1
TENSILE STRENGTH	6min	MPa	UNE-ISO 37
ELONGATION	200 min	%	UNE-ISO 37
COMPRESION SET (24h/70°C)	30 Mean values	%	UNE-ISO 815-1
AGEING HARDNESS (72h/70°C)	+2 Mean values	°ShA	DIN ISO 7619-1
AGEING TENSILE STRENGTH (72h/70°C)	-1 Mean values	%	UNE-ISO 37
AGEING ELONGATION (72h/70°C)	-10 Mean values	%	UNE-ISO 37
WORKING TEMPERATURE	-20/+100	°C	

CHEMICAL RESISTANCE		
OZONE RESISTANCE	MODERATE	
WEATHER RESISTANCE	MODERATE	
OIL RESISTANCE	LOW	
ACID RESISTANCE	MODERATE	
BASE RESISTANCE	MODERATE	

The technical information contained in this data sheet is the result of performing tests on laboratory samples according to the standards mentioned above. The customer is responsible for evaluating the suitability of the product according to their specific requirements. Values may be updated without prior notice.

[www.idcrubber.com](http://www.idcrubber.com)